



EV12-75 (12V 75Ah)

Miton
ACCU'S EN BATTERIJEN**Specifications**





Cells Per Unit	6
Voltage Per Unit	12
Nominal Capacity	75Ah@10hr-rate to 1.80V per cell @25°C
Weight	Approx. 22.5 Kg (Tolerance±3.0%)
Dimensions	Length 260 mm
	Width 169 mm
	Height 211 mm
	Total Height 216 mm
Internal Resistance	Approx. 7.0 mΩ
Terminal	T6
Layout	1
Max. Discharge Current	750A (5 sec)
Cold Cranking Ampere (CCA)	470A
Max. Charging Current	22.5A
Reference Capacity	C3 58.2AH
	C5 65.5AH
	C10 75.0AH
	C20 79.4AH
Float Charging Voltage	13.6 V~13.8 V @ 25°C Temperature Compensation: -3mV/°C/Cell
Cycle Use Voltage	14.6 V~14.8 V @ 25°C Temperature Compensation: -4mV/°C/Cell
Operating Temp. Range	Discharge: -20°C~60°C
	Charge: 0°C~50°C
	Storage: -20°C~60°C
Nominal Operating Temp. Range	25°C±5°C
Self Discharge	Valve Regulated Lead Acid (VRLA) batteries can be stored for up to 6 months at 25°C and then recharging is recommended. Monthly Self-discharge ratio is less than 3% at 25°C. Please charged batteries before using.
Container Material	A.B.S. UL94-HB, UL94-V0 Optional.

**Description and Features**

VRLA EV Series is specially designed for frequent discharge in deep cycle applications. EV batteries offer reliable performance in high load situations and have a high cycle durability due to the specially designed active material, strong grids and thick plate construction. The addition of carbon ensures faster full recharging of the battery and longer battery life. This stable and durable battery is completely sealed and maintenance free.

Features

- Absorbent Glass Mat technology
- Long service life – 50% more cycles than VRLA AGM
- Faster full recharging – quick use of application
- Suitable for (deep) cycle applications

Layout**Terminal****UL certification****Constant Current Discharge Characteristics: A (25°C)**


F.V/Time	10 Min	15 Min	30 Min	1 Hr	2 Hr	3 Hr	4 Hr	5 Hr	8 Hr	10 Hr	20 Hr
1.60V	190.4	143.2	83.8	46.3	27.3	21.2	16.6	14.2	9.52	7.91	4.14
1.65V	179.9	136.9	80.4	44.7	26.5	20.5	16.2	13.8	9.41	7.82	4.07
1.70V	165.6	128.3	76.9	43.2	25.6	20.0	15.8	13.4	9.27	7.70	4.02
1.75V	151.6	119.3	73.5	41.7	24.7	19.4	15.3	13.1	9.14	7.60	3.97
1.80V	137.2	110.2	70.2	40.1	23.8	18.8	14.9	12.8	8.98	7.50	3.94
1.85V	112.1	91.4	60.5	35.9	21.8	17.4	13.9	11.9	8.43	7.06	3.74

Constant Power Discharge Characteristics: Wpc (25°C)


F.V/Time	10 Min	15 Min	30 Min	1 Hr	2 Hr	3 Hr	4 Hr	5 Hr	8 Hr	10 Hr	20 Hr
1.60V	323.6	250.4	152.2	87.0	51.8	40.4	32.0	27.3	18.6	15.6	8.15
1.65V	311.7	242.9	147.6	84.5	50.4	39.4	31.2	26.7	18.4	15.4	8.03
1.70V	292.2	230.9	142.5	82.2	49.0	38.5	30.5	26.1	18.2	15.2	7.94
1.75V	272.3	218.0	137.6	79.7	47.5	37.5	29.8	25.5	18.0	15.0	7.86
1.80V	250.8	204.2	132.9	77.1	46.0	36.5	29.0	25.0	17.7	14.8	7.79
1.85V	208.6	171.8	115.6	69.6	42.4	33.9	27.1	23.3	16.7	14.0	7.41

(Note) The above characteristics data are average values obtained within three charge/discharge cycle not the minimum values. The battery must be fully charged before the capacity test. The C10 should reach 95% after the first cycle and 100% after the third cycle.


Charge Characteristic Curve For Cycle Use (IIUU)




Charge Characteristic Curve For Cycle Use (IUI)




Cycle Life In Relation To Depth Of Discharge




Storage Characteristics




Discharge Characteristics Curve




Relationship Between Charging Voltage And Temperature



Relationship Of OCV And State Of Charge (20°C)



Temperature Effects On Capacity



(Note) All above information shall be changed without prior notice, Landport Batteries reserves the right to explain and update the latest information.